

TYPICAL PHYSICAL PROPERTIES:

外觀.....磚紅色

PH.....6~8

PARTICLE SIZE:

D50.....1.1~1.4 μ m

D97.....5 μ m

COMPOSITION:

TREO.....93~97%

CeO₂(Cerium Oxide).....68~75%

F.....3~5%

Suspension Treated.....Available

APPLICATION:

Precision Optical Galss

Camera Lenses

Sphere Lenses

Non-Sphere Lenses

IR Filters

OHARA#:S-BAM 3, S-TIH53, S-TIH 6

, S-PHM53, S-PHM52


Abrasion Degree of Lens 150~440

EQUIVALENT:

MIREK E-30

SHOWA DENKO A-31

Cerium Oxide Particle Size Distribution



Blue Graph-Particle Size Distribution

Red Graph-Cumulative Size Distribution

