

TYPICAL PHYSICAL PROPERTIES:

Appearance.....Reddish Brown
PH..... 6~8

PARTICLE SIZE:

D50.....2.8~3.0 μ m
D97.....8.5 μ m

COMPOSITION:

TREO.....95%
CeO₂(Cerium Oxide).....60%
F.....3~5 %
Suspension Treated.....Available


APPLICATION:

Ohara Code:S-LAH65, S-LAH59, S-LAH55, S-LAH58,
S-LAM66,S-NSL36,S-BAL42,S-TIL25,S-TIL27
S-BSM14,BK7
Abrasion Degree of Lens 50~135

EQUIVALENT:

CEPOL 132

Cerium Oxide Particle Size Distribution



Blue Graph-Particle Size Distribution
Red Graph-Cumulative Size Distribution

