

TYPICAL PHYSICAL PROPERTIES:

Appearance.....White
 PH.....6.0~8.0
 Density..... g/cm³

PARTICLE SIZE:

D50.....1.8~2.2 μ m
 D97.....5.0 μ m

COMPOSITION:

TREO.....over 95%
 CeO₂(Cerium Oxide).....over 65%
 F.....5%


APPLICATION:

Plano Optic
 Round Optic
 Fibre Optic
 Ohara Code:S-LAH65, S-LAH59, S-LAH55, S-LAH58,
 S-LAH64, S-LAM54, S-LAH66, S-LAM60, S-LAH53
 , S-LAH60, S-LAH51, S-LAH52, S-LAH63, S-LAM66
 Abrasion Degree of Lens 50~100

EQUIVALENT:

CEPOL 201

Cerium Oxide Particle Size Distribution



Blue Graph-Particle Size Distribution
 Red Graph-Cumulative Size Distribution

